

SKF Bearing Grease

General purpose, high load industrial bearing grease

LGNL 2

SKF LGNL 2 is a mineral oil based, anhydrous calcium soap thickened grease suitable for high load applications. This general purpose wide applications grease is an effective alternative for traditional general purpose and extreme pressure lithium based greases.

- Excellent water resistance and corrosion protection
- Good mechanical stability
- Good pumpability
- Excellent wear protection

Typical applications

- Agricultural equipment
- Conveyors
- Vibrating applications
- Mills and crushers

Available pack sizes		
Packsize	Designation	SKF
420 ml cartridge	LGNL 2/0.4	El Mi
18 kg pail	LGNL 2/18	
180 kg drum	LGNL 2/180	







Technical data			
Designation	LGNL 2/(pack size)		
DIN 51825 code	KP2K-30	Corrosion protection	
NLGI consistency class	2	Emcor: – standard ISO 11007	0-0
Thickener	Anhydrous calcium	 water washout test 	0-0
Colour	Yellow brown	Water resistance DIN 51 807/1, 3 hrs at 90 °C	1 max.
Base oil type	Mineral		1 max.
Operating temperature range	−30 to +110 °C (−22 to +230 °F)	Oil separation DIN 51 817, 7 days at 40 °C, %	1-5
Dropping point DIN ISO 2176	140 °C min. (284 °F min.)	Lubrication ability	
Base oil viscosity		R2F, running test B at 120 °C	Pass
40 °C, mm²/s 100 °C, mm²/s	220 14	Copper corrosion DIN 51 811	2 max. at 100 °C (<i>212 °F</i>)
Penetration DIN ISO 2137 60 strokes, 10 ⁻¹ mm	265-295	Rolling bearing grease life	
100 000 strokes, 10 ⁻¹ mm	+50 max.	ROF test, L50 life at 10 000 r/min., hrs	1 000 min. at 110 °C (230 °F)
Mechanical stability Roll stability,		EP performance	
50 hrs at 80 °C, 10 ⁻¹ mm	+70 max.	Wear scar DIN 51350/5, 1 400 N, mm	1.8 max
V2F test	'M'	4-ball test, welding load DIN 51350/4. N	2 800 min.
		Shelf life	5 years
These characteristics represent typ	pical values.		

which must set in	TIC - CARL		
interest conditions	Select on application conditions		
ed Index and an Index Index	treasure (and)	Wing Take Strate, Jonated Ker Stiff (Proper Sciences Strategistics) (Pro	
na mana an ann '' a na Anna ann an Anna '' a na Anna anna anna anna anna Anna anna a	Annu share a s	hand 2019년 전 1841 (1945) 전 3월 1945 (1945) 전 3월 1946 (1946) 전 3899 (1946)	
	Deer regionegenieren Tepenieren progenieren (here en) Richard Bergenieren (here) Richard (here) Anteren (here) Richard (here)	The second secon	

Advanced tool for grease selection and relubrication calculation

LubeSelect for SKF greases

Selecting a suitable grease for a particular bearing is a crucial step if the bearing is to meet design expectations in its application. SKF knowledge about bearing lubrication has been encapsulated into a computer program that can be consulted at skf.com/lubeselect

LubeSelect for SKF greases provides you a user friendly tool to select the right grease and suggest frequency and quantity, while taking into account the particular conditions of your application. General guidelines for typical greases for different applications are also available.



Scan or click the QR code, or go to skf.com/lubeselect

skf.com | skf.com/lubrication | skf.com/mapro

SKF is a registered trademark of AB SKF (publ).

© SKF Group 2023 . All rights reserved. Please note that this publication may not be copied ordistributed, in whole or in part, unless prior written permission is granted.

Every care has been taken to ensure the accuracy of the information contained in this publication, but no liability can be accepted for any loss or damage whether direct, indirect or consequential arising out of the use of the information contained herein.

PUB MP/P8 19614 EN · May 2023

Certain image(s) used under license from Shutterstock.com.